

#### LA-UR-18-27262

Approved for public release; distribution is unlimited.

Tuning the ferromagnetic tri-critical point and quantum critical point in Ce(Pd1-xNix)2P2 under high magnetic fields Title:

Author(s): Lai, You

Intended for: LANL student symposium

Issued: 2018-07-31



# Tuning the ferromagnetic tri-critical point and quantum critical point in Ce(Pd<sub>1-x</sub>Ni<sub>x</sub>)<sub>2</sub>P<sub>2</sub> under high magnetic fields

You Lai<sup>1,2</sup>, Laurel E. Winter<sup>2</sup>, F. Weickert<sup>1,2</sup>, Ryan E. Baumbach<sup>1</sup>, Ross D. McDonald<sup>2</sup>

- 1. Florida State University National High Magnetic Field Laboratory
- 2. Los Alamos National Laboratory National High Magnetic Field Laboratory

### Introduction

We recently uncovered a ferromagnetic quantum phase transition in the Kondo lattice alloy series  $Ce(Pd_{1-x}Ni_x)_2P_2$  near  $x_{cr} \approx 0.7$  (Fig. 1a). This provides the rare opportunity to study phenomena associated with ferromagnetic quantum fluctuations and to contrast them with predictions from different theories: e.g., such as those proposed by Belitz, Kirkpatrick, and Vojta (BKV) [1-5]. In particular, the BKV theory predicts that for clean systems there is a tri-critical point separating a high temperature line of second order phase transitions from a low temperature line of first order phase transitions, where the application of a magnetic field produces winglike second order phase boundaries that intercept zero temperature (Fig. 1b). With increasing disorder (e.g., through alloying), the tri-critical Fig. 2 Sample with Focused Ion Beam structure point is pushed to zero temperature and the second order phase boundary For x = 0.83: right above the critical x-region extends all the way to zero temperature (Fig. 1c). This has spurred interest in ferromagnetic quantum criticality in disordered metals like Ce(Pd<sub>1-x</sub>Nix)<sub>2</sub>P<sub>2</sub>, where a possibility is that they might host anomalous important for measurements in pulsed fields because metallic states and even unconventional superconductivity. Here we report there are many noise sources from the pulsed field initial results from magnetoresistance and tunnel diode oscillator measurement: measurement near  $x \approx x_{cr}$ , to probe whether the wing-like and/or anomalous electrical transport appears in the critical region.





Fig. 1 (a) T-x Phase diagram: Curie temperature  $T_{\rm C}$  is suppressed linearly with x, resulting in a ferromagnetic quantum phase transition near  $x_{cr} = 0.7$ . The main tuning parameters are unit cell volume and disorder. Near  $x_{cr}$  the Fermi liquid behavior breaks down. (b) **BKV** *T-P-H* phase diagram for clean FM-QPT: Universal phase diagram features 2<sup>nd</sup> order to 1<sup>st</sup> order phase boundary separated by tri-critical point. (c) BKV T-P-H phase diagram for disordered FM-QPT: Disorder suppresses the tri-critical point and 2<sup>nd</sup> order phase transition goes to zero temperature. [1-5]

FIELD LABORATORY

## Magnetoresistance

 $Ce(Pd_{1-x}Ni_x)_2P_2$  x = 0.83



Electrical Resistance  $R = \rho L/A$ After FIBing, R increases by an order of 10. This is

- (1)Pulse magnet itself
- (2) Taking data at high frequency
- (3) Contact resistance
- (4) Vibration from the cryogen system and magnet




Fig.3 Magnetoresistance for  $Ce(Pd_{1-x}Ni_x)_2P_2 x = 0.83$ 

- Crossover-like behavior with T and H
- No evidence for the "wing" behavior expected from clean BKV phase diagram.

# Tunnel Diode Oscillator [6]





Fig. 4 TDO measurement setup

Fig. 5 TDO sample mounted

$$f_0 + \Delta f = \frac{2\pi\sqrt{L_{\rm t}C_{\rm t}}}{2\pi\sqrt{(L_{\rm tot} + \Delta L_{\rm t})C}}$$

Assume  $\Delta L$  is sufficiently small we can Taylor expand to first order

$$rac{\Delta f}{f_0} pprox -rac{1}{2} rac{\Delta L_{
m c}}{L_{
m c}}, \quad rac{\Delta f}{f_0} pprox -rac{1}{2} rac{V_s}{V_c} \chi_c$$
 $rac{\Delta f}{f} = -G rac{\Delta \delta}{c}, \quad \delta = \sqrt{
ho/\pi \mu f}$ 



### Fig.6 TDO measurement on several samples under pulsed fields


- ➤ No quantum oscillation found for CePd₂P₂ or CePd₂-xNixP₂, Cleaner sample as well as lower T and larger H are needed.
- The data did not show much T dependence and there is no field induced phase transition.

# Conclusions and Future work

- > As predicted by BKV, if there is enough disorder the wings will not be observed
- Magnetoresistance, TDO or torque measurement on sample close to the FM-QCP are planned



- 1. M. Brando *et al.* , Rev. Mod. Phys. **88**, 025006 (2016). 2. T. R. Kirkpatrick and D. Belitz, Phys. Rev. B 85, 134451 (2012). 3. D. Belitzet al., Phys. Rev. Lett. 82, 4707 (1999).
- 4. D. Belitzet al., Phys. Rev. Lett. 94, 247205 (2005). 5. T. R. Kirkpatrick and D. Belitz, Phys. Rev. B **91**, 214407 (2015) 6. Laurel E. Winter dissertation.





We gratefully acknowledge the support of the U.S. Department of Energy through the LANL/LDRD Program and the G. T. Seaborg LOŚ Alamos Institute for this work. A portion of this work was performed at the National High Magnetic Field Laboratory, which is supported by the National Science Foundation Cooperative Agreement No. DMR-1157490 and the State of Florida. A portion of this work was supported by the Center for Actinide Science and Technology (CAST), an Energy Frontier Research Center (EFRC) funded by the U.S. DOE, Office of Science, Basic Energy Sciences (BES), under Award No. DE-SC0016568. LA-UR#